



Solar Compounds Corporation  
1201 West Blancke Street  
Linden, NJ 07036 USA  
Ph: 908-862-2813 Fax: 908-862-8061  
Intl: Ph: (0101) 908-862-2813 Fax: (0101) 908-862-8061  
www.solarcompounds.com

# TECHNICAL DATA SHEET

## SOLARITE KM-130

**DESCRIPTION:** **KM-130** is a rubber-based asphalt modifier designed specifically for easy incorporation into basic and oxidized asphalts under slow speed mixing conditions to impart flexibility and improved tack to the finished product. **KM-130** avoids the need for high shear rubber mixers in large scale asphalt operations, significantly improving batch cycle times and product consistency.

### **PHYSICAL PROPERTIES:**

Color.....Black  
Viscosity @ 300°F Brookfield  
Thermocel ASTM-D-2196.....200 to 300 cps  
Softening Point (°F) ASTM-D-3695.....170 to 200  
Cone Penetration in 16 oz. Tin  
(0.1mm) @ 25°C.....180 to 200  
Specific Gravity @ 77°F.....8.4 Lbs. Per Gallon

### **IMPORTANT:**

The following supersedes any provision in your company's forms, letters, and papers. **SOLAR COMPOUNDS CORPORATION** makes NO WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES of MERCHANTABILITY OR of FITNESS FOR A PARTICULAR PURPOSE FOR THIS PRODUCT. No statements or recommendations contained in the product literature are to be construed as inducements to infringe any relevant patent, now or thereafter in existence. UNDER NO CIRCUMSTANCES SHALL **SOLAR COMPOUNDS CORPORATION** BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL OR OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH of WARRANTY, STRICT LIABILITY OR ANY OTHER THEORY, ARISING OUT of THE USE OR HANDLING of THIS PRODUCT. The sole liability of **SOLAR COMPOUNDS CORPORATION** for any claims arising out of the manufacture, use or sale of its products shall be to refund the buyer's purchase price, provided such products have been demonstrated in **SOLAR COMPOUNDS CORPORATION'S** sole opinion, to justify such refund.

**HEALTH CAUTION:**

Please refer to Material Safety Data Sheet before using these products.

**PLEASE REFER TO MATERIAL SAFETY DATA SHEET FOR FURTHER FIRST  
AID INFORMATION.**

FOR CHEMICAL EMERGENCY  
CALL CHEMTREC (DAY OR NIGHT) 800-424-9300.