



Solar Compounds Corporation  
1201 West Blancke Street  
Linden, NJ 07036 USA  
Ph: 908-862-2813 Fax: 908-862-8061  
Intnl: Ph: (0101) 908-862-2813 Fax: (0101) 908-862-8061  
www.solarcompounds.com

# TECHNICAL DATA SHEET

## SOLARITE EA- 0463

**DESCRIPTION:** Solarite EA- 0463 is a room temperature curing 1 to 1 by volume adhesive compound, whose convenient mixing ratio makes it easy to use and well suited to automatic dispensing equipment. Solarite EA- 0463 give a semi-rigid high impact resistant epoxy with excellent adhesion to metals, composites and plastics.

### SPECIFICATIONS—UNCURED:

	<b>Part A</b>	<b>Part B</b>
Color, Visual	Off White	Amber
Mix Ratio—By Weight	100	72
Mix Ratio—By Volume	1	1
Viscosity, cps, ASTM-D-2393	2,000	11,000
Specific Gravity	1.32	0.97
Gel Time, 25°C, Hours		3-4
Mixed Viscosity, cps, ASTM-D-1084		5,000
Shelf Life, 25°C, Months		12

### SPECIFICATIONS—CURED:

#### PHYSICAL:

Durometer, ASTM-D-2240	80-85D
Compressive Strength, psi, ASTM-D-695	12,675
Tensile Strength, psi, ASTM-D-638	7,300
Tensile Elongation, Percentage, ASTM-D-638	5.0
Service Temperature, °C	105

### **USE INSTRUCTIONS:**

1. Pre-mix contents of each container before use to ensure the entire contents are uniform. Some settling may occur upon prolonged storage which is soft and easily incorporated.
2. Measure out equal components of the product by volume and mix thoroughly together to incorporate any settled material.
3. De- air if necessary at 760 mm of Hg for 5-10 minutes.
4. Pour into cavity to be encapsulated.

### **CURE SCHEDULE:**

Initial cure is achieved in 16-24 hours at room temperature. Final cure takes at least 7-10 days at 72F. To accelerate the cure higher temperatures can be used, 2-4 hours at 150 F is usually sufficient , after allowing the product to gel at room temperature for 3 hours.

### **STORAGE REQUIREMENTS:**

This product has a slight tendency to settle upon storage and shipment, material should be mixed well prior to use. Store in a cool dry place.

### **IMPORTANT:**

The following supersedes any provision in your company's forms, letters, and papers. **SOLAR COMPOUNDS CORPORATION** makes NO WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES of MERCHANTABILITY OR of FITNESS FOR A PARTICULAR PURPOSE FOR THIS PRODUCT. No statements or recommendations contained in the product literature are to be construed as inducements to infringe any relevant patent, now or thereafter in existence. UNDER NO CIRCUMSTANCES SHALL **SOLAR COMPOUNDS CORPORATION** BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL OR OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH of WARRANTY, STRICT LIABILITY OR ANY OTHER THEORY, ARISING OUT of THE USE OR HANDLING of THIS PRODUCT. The sole liability of **SOLAR COMPOUNDS CORPORATION** for any claims arising out of the manufacture, use or sale of its products shall be to refund the buyer's purchase price, provided such products have been demonstrated in **SOLAR COMPOUNDS CORPORATION'S** sole opinion, to justify such refund.

### **HEALTH CAUTION:**

Avoid breathing possible fumes, mists and vapors, which can cause severe respiratory damage. Use of NIOSH approved breathing apparatus is required for more than minimal exposure. Always work in areas with adequate ventilation to allow dissipation of polyamine and other chemical fumes, and where applicable, solvent fumes. Use of goggles, protective garments, rubber gloves, protective cream is required. If material gets into eyes, flush thoroughly with clear water for twenty (20) minutes; then seek medical treatment. Avoid skin contact. Material can cause contact dermatitis. Always wash exposed areas immediately, using warm water and soap, followed by rinsing with clean water. Observe all safety precautions. It is important when using solvent based materials or solvents to keep away from open flame or ignition source.

**PLEASE REFER TO MATERIAL SAFETY DATA SHEET FOR FURTHER FIRST AID INFORMATION.**

FOR CHEMICAL EMERGENCY  
CALL CHEMTREC (DAY OR NIGHT) 800-424-9300.

2/01