



Solar Compounds Corporation
1201 West Blancke Street
Linden, NJ 07036 USA
Ph: 908-862-2813 Fax: 908-862-8061
Intl: Ph: (0101) 908-862-2813 Fax: (0101) 908-862-8061
www.solarcompounds.com

TECHNICAL DATA SHEET

SOLARITE EA- 0566 BLACK

DESCRIPTION: Solarite EA- 0566 is a semi-flexible epoxy adhesive compound, with excellent strength under static and dynamic loading. EA- 0566 is designed for bonding fiberglass laminations to wood and polyolefin plastics associated with ski and snowboard construction. A heat cure is recommended for optimal properties .

SPECIFICATIONS—UNCURED:

	Part A	Part B
Color, Visual	Black	Amber
Mix Ratio - By Weight	100	40
Mix Ratio - By Volume	100	49
Viscosity, cps, ASTM-D-2393	8,000	1,600
Specific Gravity	1.15	0.95
Gel Time, 25°C, Hours		0.5-0.7
Mixed Viscosity, cps, ASTM-D-1084		3,500
Shelf Life, 25°C, Months		12

SPECIFICATIONS—CURED:

PHYSICAL:

Durometer, ASTM-D-2240	80D
Compressive Strength, psi, ASTM-D-695	16,100
Tensile Strength, psi, ASTM-D-638	5600
Lap Shear,psi ,Steel/Steel	2400
Peel Strength,lb/in ,avg.	6-15

USE INSTRUCTIONS:

1. Pre-mix contents of each container before use to ensure the entire contents are uniform. Measure out components of the product by weight and mix thoroughly together to incorporate any settled material.
2. De- air if necessary at 760 mm of Hg for 5-10 minutes.

CURE SCHEDULE:

Initial cure is achieved in 16-24 hours at room temperature. Final cure takes at least 7-10 days at 72F. To accelerate the cure higher temperatures can be used, 10-15 minutes at 190 F is usually sufficient .,

STORAGE REQUIREMENTS:

Store in a cool dry place.

IMPORTANT:

The following supersedes any provision in your company's forms, letters, and papers. **SOLAR COMPOUNDS CORPORATION** makes NO WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES of MERCHANTABILITY OR of FITNESS FOR A PARTICULAR PURPOSE FOR THIS PRODUCT. No statements or recommendations contained in the product literature are to be construed as inducements to infringe any relevant patent, now or thereafter in existence. UNDER NO CIRCUMSTANCES SHALL **SOLAR COMPOUNDS CORPORATION** BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL OR OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH of WARRANTY, STRICT LIABILITY OR ANY OTHER THEORY, ARISING OUT of THE USE OR HANDLING of THIS PRODUCT. The sole liability of **SOLAR COMPOUNDS CORPORATION** for any claims arising out of the manufacture, use or sale of its products shall be to refund the buyer's purchase price, provided such products have been demonstrated in **SOLAR COMPOUNDS CORPORATION'S** sole opinion, to justify such refund.

HEALTH CAUTION:

Avoid breathing possible fumes, mists and vapors, which can cause severe respiratory damage. Use of NIOSH approved breathing apparatus is required for more than minimal exposure. Always work in areas with adequate ventilation to allow dissipation of polyamine and other chemical fumes, and where applicable, solvent fumes. Use of goggles, protective garments, rubber gloves, protective cream is required. If material gets into eyes, flush thoroughly with clear water for twenty (20) minutes; then seek medical treatment. Avoid skin contact. Material can cause contact dermatitis. Always wash exposed areas immediately, using warm water and soap, followed by rinsing with clean water. Observe all safety precautions. It is important when using solvent based materials or solvents to keep away from open flame or ignition source.

PLEASE REFER TO MATERIAL SAFETY DATA SHEET FOR FURTHER FIRST AID INFORMATION.

FOR CHEMICAL EMERGENCY
CALL CHEMTREC (DAY OR NIGHT) 800-424-9300.