



Solar Compounds Corporation
1201 West Blancke Street
Linden, NJ 07036 USA
Ph: 908-862-2813 Fax: 908-862-8061
Intnl: Ph: (0101) 908-862-2813 Fax: (0101) 908-862-8061
www.solarcompounds.com

TECHNICAL DATA SHEET

SOLARITE SI-224 GEL-T

DESCRIPTION: Solarite SI-224 Gel-T is a thixotropic general purpose 1 to 1 by volume or weight RTV(Room temperature vulcanizing) silicone potting compound. The convenient mixing ratio makes it easy to use and well suited to automatic dispensing equipment. SI-224 Gel-T produce high gloss and void free castings when potting electrical component. For softer gels less Part B can be added and harder gels more Part B can be added. The cured gel provides excellent vibration damping and mechanical cushioning for sensitive electronics and is re-enterable for component repair. Also available is Solarite SI-223 Gel a low viscosity pourable grade. NOTE: Custom formulas are available for thermal conductivity, fire retardency, cure speed and color-coding .

SPECIFICATIONS—UNCURED:

	Part A	Part B
Color, Visual	Opaque	Opaque
Mix Ratio—By Weight	1	1
Mix Ratio—By Volume	1	1
Specific Gravity	0.98	0.98
Gel Time, 25°C, Hours		2-3
Mixed Viscosity, cps, ASTM-D-1084		Thixotropic
Shelf Life, 25°C, Months		12

SPECIFICATIONS—CURED:

PHYSICAL:

Penetration, mm , 50 gram mass	8.9
Durometer, ASTM-D-2240	Less than zero Shore A
Tensile Elongation, Percentage, ASTM-D-638	125
Thermal Conductivity, BTU-in/ft ² (Hour) (°F)	0.10
Service Temperature, °C	-55 to 200

ELECTRICAL PROPERTIES:

Dielectric Strength, Volts/Mil, ASTM-D-149	515
Dielectric Constant, 1 kHz, ASTM-D-150	2.9
Dissipation Factor, 1 kHz, ASTM-D-150	0.001
Volume Resistivity, ohm/cm, ASTM-D-257	1x10 ¹⁵

USE INSTRUCTIONS:

1. Pre-mix contents of each container before use to ensure the entire contents are uniform.
2. Measure out equal components of the product by weight or volume and mix thoroughly together to incorporate any settled material.
3. De- air if necessary at 760 mm of Hg for 5-10 minutes.
4. Pour into cavity to be encapsulated.

CURE SCHEDULE:

Initial cure is achieved in 16-24 hours at room temperature. To accelerate the cure higher temperatures can be used, 2-4 hours@150 F is usually sufficient or 1 [hour@190F](#) or 15 minutes@250F.

NOTE: SI-224 Gel-T when placed in contact with certain materials may inhibit the cure. Anything that contains amines, amine cured epoxies, and tin cured silicones can cause poisoning. It is strongly recommended to test surface to be potted if in doubt.

STORAGE REQUIREMENTS:

Store in a cool dry place.

IMPORTANT:

The following supersedes any provision in your company's forms, letters, and papers. **SOLAR COMPOUNDS CORPORATION** makes NO WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES of MERCHANTABILITY OR of FITNESS FOR A PARTICULAR PURPOSE FOR THIS PRODUCT. No statements or recommendations contained in the product literature are to be construed as inducements to infringe any relevant patent, now or thereafter in existence. UNDER NO CIRCUMSTANCES SHALL **SOLAR COMPOUNDS CORPORATION** BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL OR OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH of WARRANTY, STRICT LIABILITY OR ANY OTHER THEORY, ARISING OUT of THE USE OR HANDLING of THIS PRODUCT. The sole liability of **SOLAR COMPOUNDS CORPORATION** for any claims arising out of the manufacture, use or sale of its products shall be to refund the buyer's purchase price, provided such products have been demonstrated in **SOLAR COMPOUNDS CORPORATION'S** sole opinion, to justify such refund.

HEALTH CAUTION:

Avoid breathing possible fumes, mists and vapors, which can cause severe respiratory damage. Use of NIOSH approved breathing apparatus is required for more than minimal exposure. Always work in areas with adequate ventilation to allow dissipation of polyamine and other chemical fumes, and where applicable, solvent fumes. Use of goggles, protective garments, rubber gloves, protective cream is required. If material gets into eyes, flush thoroughly with clear water for twenty (20) minutes; then seek medical treatment. Avoid skin contact. Material can cause contact dermatitis. Always wash exposed areas immediately, using warm water and soap, followed by rinsing with clean water. Observe all safety precautions. It is important when using solvent based materials or solvents to keep away from open flame or ignition source.

PLEASE REFER TO MATERIAL SAFETY DATA SHEET FOR FURTHER FIRST AID INFORMATION.

FOR CHEMICAL EMERGENCY
CALL CHEMTREC (DAY OR NIGHT) 800-424-9300.