



Solar Compounds Corporation
1201 West Blancke Street
Linden, NJ 07036 USA
Ph: 908-862-2813 Fax: 908-862-8061
Intnl: Ph: (0101) 908-862-2813 Fax: (0101) 908-862-8061
www.solarcompounds.com

TECHNICAL DATA SHEET

SOLARITE EP- 0575

DESCRIPTION: Solarite EP- 0575 is a low viscosity room temperature curing epoxy potting and casting compound, whose convenient mixing ratio makes it easy to use and well suited to automatic dispensing equipment. EP- 0575 produces high gloss void free castings when potting electrical components.

SPECIFICATIONS—UNCURED:

	Part A	Part B
Color, Visual	Black	Clear
Mix Ratio—By Weight	100	20
Mix Ratio—By Volume	3	1
Viscosity, cps, ASTM-D-2393	8,000	60
Specific Gravity	1.60	0.96
Gel Time, 25°C, Hours	0.75-1.00	
Mixed Viscosity, cps, ASTM-D-1084	1,200	
Shelf Life, 25°C, Months	12	

SPECIFICATIONS—CURED:

PHYSICAL:

Durometer, ASTM-D-2240	85D
Tensile Strength, psi, ASTM-D-638	4,300
Tensile Elongation, Percentage, ASTM-D-638	7.0
Thermal Conductivity, BTU-in/ft ² (Hour) (°F)	3.4

ELECTRICAL PROPERTIES:

Dielectric Strength, Volts/Mil, ASTM-D-149	422
Dielectric Constant, 1 kHz, ASTM-D-150	4.12
Dissipation Factor, 1 kHz, ASTM-D-150	0.02
Volume Resistivity, ohm/cm, ASTM-D-257	1x10 ¹⁴

USE INSTRUCTIONS:

1. Pre-mix contents of each container before use to ensure the entire contents are uniform. Some settling may occur upon prolonged storage which is soft and easily incorporated.
2. Measure out components of the product by weight or volume and mix thoroughly together to incorporate any settled material.
3. De- air if necessary at 760 mm of Hg for 5-10 minutes.
4. Pour into cavity to be encapsulated.

CURE SCHEDULE:

Initial cure is achieved in 16-24 hours at room temperature. Final cure takes at least 7-10 days at 72F. To accelerate the cure higher temperatures can be used, 2-4 hours at 150 F is usually sufficient , after allowing the product to gel at room temperature for 3 hours.

STORAGE REQUIREMENTS:

This product has a tendency to settle upon storage and shipment, material should be mixed well prior to use. Store in a cool dry place.

IMPORTANT:

The following supersedes any provision in your company's forms, letters, and papers. **SOLAR COMPOUNDS CORPORATION** makes NO WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES of MERCHANTABILITY OR of FITNESS FOR A PARTICULAR PURPOSE FOR THIS PRODUCT. No statements or recommendations contained in the product literature are to be construed as inducements to infringe any relevant patent, now or thereafter in existence. UNDER NO CIRCUMSTANCES SHALL **SOLAR COMPOUNDS CORPORATION** BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL OR OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH of WARRANTY, STRICT LIABILITY OR ANY OTHER THEORY, ARISING OUT of THE USE OR HANDLING of THIS PRODUCT. The sole liability of **SOLAR COMPOUNDS CORPORATION** for any claims arising out of the manufacture, use or sale of its products shall be to refund the buyer's purchase price, provided such products have been demonstrated in **SOLAR COMPOUNDS CORPORATION'S** sole opinion, to justify such refund.

HEALTH CAUTION:

Avoid breathing possible fumes, mists and vapors, which can cause severe respiratory damage. Use of NIOSH approved breathing apparatus is required for more than minimal exposure. Always work in areas with adequate ventilation to allow dissipation of polyamine and other chemical fumes, and where applicable, solvent fumes. Use of goggles, protective garments, rubber gloves, protective cream is required. If material gets into eyes, flush thoroughly with clear water for twenty (20) minutes; then seek medical treatment. Avoid skin contact. Material can cause contact dermatitis. Always wash exposed areas immediately, using warm water and soap, followed by rinsing with clean water. Observe all safety precautions. It is important when using solvent based materials or solvents to keep away from open flame or ignition source.

PLEASE REFER TO MATERIAL SAFETY DATA SHEET FOR FURTHER FIRST AID INFORMATION.

FOR CHEMICAL EMERGENCY
CALL CHEMTREC (DAY OR NIGHT) 800-424-9300.