



Solar Compounds Corporation
1201 West Blancke Street
Linden, NJ 07036 USA
Ph: 908-862-2813 Fax: 908-862-8061
Intl: Ph: (0101) 908-862-2813 Fax: (0101) 908-862-8061
www.solarcompounds.com

TECHNICAL DATA SHEET

SOLARITE KM-4408-RV UNFILLED ASPHALT ELECTRICAL POTTING COMPOUND

DESCRIPTION: KM-4408-RV is an unfilled oxidized petroleum asphalt potting compound designed for low-cost encapsulation designs such as power suppliers and transformers. KM-4408-RV is easy to pour and yields a semi-rigid high softening point product when cooled to room temperature.

PHYSICAL PROPERTIES:

Color.....Black
Viscosity Brookfield Thermocel
@ 300°F ASTM-D-2186.....550 to 950 cps
Softening Point (°F) ASTM-D-3695.....258 to 268
Penetration (Needle 0.1mm)
@ 77°F 5 Seconds.....0 to 2

IMPORTANT:

The following supersedes any provision in your company's forms, letters, and papers. **SOLAR COMPOUNDS CORPORATION** makes NO WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES of MERCHANTABILITY OR of FITNESS FOR A PARTICULAR PURPOSE FOR THIS PRODUCT. No statements or recommendations contained in the product literature are to be construed as inducements to infringe any relevant patent, now or thereafter in existence. UNDER NO CIRCUMSTANCES SHALL **SOLAR COMPOUNDS CORPORATION** BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL OR OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH of WARRANTY, STRICT LIABILITY OR ANY OTHER THEORY, ARISING OUT of THE USE OR HANDLING of THIS PRODUCT. The sole liability of **SOLAR COMPOUNDS CORPORATION** for any claims arising out of the manufacture, use or sale of its products shall be to refund the buyer's purchase price, provided such products have been demonstrated in **SOLAR COMPOUNDS CORPORATION'S** sole opinion, to justify such refund.

HEALTH CAUTION:

Please refer to Material Safety Data Sheet before using these products.

**PLEASE REFER TO MATERIAL SAFETY DATA SHEET FOR FURTHER FIRST
AID INFORMATION.**

FOR CHEMICAL EMERGENCY
CALL CHEMTREC (DAY OR NIGHT) 800-424-9300.