



Solar Compounds Corporation
1201 West Blancke Street
Linden, NJ 07036 USA
Ph: 908-862-2813 Fax: 908-862-8061
Intl: Ph: (0101) 908-862-2813 Fax: (0101) 908-862-8061
www.solarcompounds.com

TECHNICAL DATA SHEET

SOLARITE KM-2730 STRAND SEAL SEMI-CONDUCTING

END USE: A semi hardening sealant for high voltage power cable strands to prohibit the entrance of water and gas.

DESCRIPTION: SOLARITE KM-2730 is composed of a high-molecular weight plasticizer, synthetic polymers and conductive fillers . All ingredients are virgin materials; no inert fillers.

PHYSICAL PROPERTIES:

Color.....Black
Solids.....100%
Specific Gravity..... .98 +/- .05
Resistivity ohms/Unit Sq.....<1000 ohms
Penetration (.1mm)
(Cone, 300 grams ld. @ 77°F
ASTM-D-217-48).....50 to 65
Melt Index @ 150°C
(Min. 2160 Gm Load, Preheat 10 Mins.,
Run 30 Sec.).....40 to 70 Gms/10 Min.
Thermal Volumetric Expansion*
Through 440°F.....10% Max.

SPECIAL PROPERTIES:

- 1) Semi-hardening, remains plastic with no shrinkage upon aging.
- 2) Non-injurious to crosslinked polyethylene and EPDM Semi-Conducting shields.
- 3) No adverse effects on electrical or physical properties of high molecular weight, high and low density polyethylene, synthetic elastomers, crosslinked polymers, P.V.C. and rubbers.

- 4) Remains stable at 300°F and higher temperatures for short periods.
- 5) Non-bleeding.
- 6) Non-hygroscopic, excellent resistance to water, water vapor, and salt water.
- 7) Non-corrosive to metals.
- 8) Flexible at -40°F.
- 9) Little to no odor, presents no toxicological or dermatological problems.
- 10) Will not liquefy or flow at the higher temperatures.
- 11) Compliance with ANSI 119.4 Connectability Standard.

APPLICATION: Pumped with heavy duty, double-action hydraulic drum ram equipment. Cone-shaped, heated follower plate, and heated delivery lines recommended. Recommended processing temperatures--275°F to 300°F.

PACKAGING: 55-gallon drums; 5 gallon pails.

***THERMAL EXPANSION PROCEDURE:** Weigh 5 to 6 grams of material, form into a noodle, and place in cylinder of melt apparatus at room temperature. Load piston with a 2060 gram dead weight and depress until (a) extrudate passes thru the die and (b) the bottom engraved line is flush with the top of the guide collar. Plug die, turn Melt Index apparatus to maximum output and start stopwatch. Measure temperature and piston rise (in 64ths of an inch) to 440°F. Using the calculations shown below, the increase in volume at 440°F shall not exceed 10 percent:

- 1) Area of cylinder base = 0.1110 square inches.
- 2) Height of cylinder occupied by sample @ RT = 1.9063 inches.
- 3) Original volume of specimen = 1.9063 inches x 0.1110 square inches or 0.2116 cubic inches.

IMPORTANT:

The following supersedes any provision in your company's forms, letters, and papers. **SOLAR COMPOUNDS CORPORATION** makes NO WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES of MERCHANTABILITY OR of FITNESS FOR A PARTICULAR PURPOSE FOR THIS PRODUCT. No statements or recommendations contained in the product

literature are to be construed as inducements to infringe any relevant patent, now or thereafter in existence. UNDER NO CIRCUMSTANCES SHALL **SOLAR COMPOUNDS CORPORATION** BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL OR OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY OR ANY OTHER THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. The sole liability of **SOLAR COMPOUNDS CORPORATION** for any claims arising out of the manufacture, use or sale of its products shall be to refund the buyer's purchase price, provided such products have been demonstrated in **SOLAR COMPOUNDS CORPORATION'S** sole opinion, to justify such refund.

HEALTH CAUTION:

Please refer to Material Safety Data Sheet before using these products.

PLEASE REFER TO MATERIAL SAFETY DATA SHEET FOR FURTHER FIRST AID INFORMATION.

FOR CHEMICAL EMERGENCY
CALL CHEMTREC (DAY OR NIGHT) 800-424-9300.