



Technical Data Sheet

Technical Data Sheet – Template



Solar Compounds Corporation • Tel: +1 (908) 862-2813 • Fax: +1 (908) 862-8061 • <http://solarcompounds.com>

SOLARITE® KM-2740 SILICONE SEALANTS

Description: Solarite KM-2740 sealants are 2-component room-temperature vulcanizing silicones with a convenient 1 to 1, by volume or weight, mix ratio. Well suited to automatic dispensing equipment used in sophisticated cabling operations. Their lightweight and excellent stripability make them ideal for sealing and blocking wire strands, cable valleys and braided shields used in the construction of power cables. Available in several standard viscosity grades and custom cure schedules.

Typical Physical Constants – Uncured:

		Part A	Part B
Color, Visual		Blue	Yellow
Mix Ratio—By Weight		1	1
Mix Ratio—By Volume		1	1
Viscosity, cps, ASTM-D-2393	KM-2740-1 (Mastic)	6-7 Million	6-7 Million
	KM-2740-2 (Paste)	0.8-2 Million	0.8-2 Million
	KM-2740-3 (Pourable)	0.2-0.3 Million	0.2-0.3 Million
	KM-2740-4 (Pourable)	35-40,000	35-40,000
	KM-2740-6 (Pourable)	190-235,000	190-235,000
Specific Gravity		0.84	0.84
Gel Time, 25°C, Hours		8-16	
Cure Time, 25°C, Hours		24-48	
Shelf Life, 25°C, Months (Product Specific)		3-6	

TYPICAL PHYSICAL CONSTANTS—UNCURED:

Durometer, ASTM-D-2240 50-85A
Halogen Content None
Oxygen Index ASTM-D-2863 54.5%
Toxicity Index, NES 713/MIL-C-24643 (Maximum-5) 3.8
Acid Gas Generation/MIL-C-24643 (Maximum-2%) 0.31
Thermal Conductivity, BTU-in/ft² (Hour) (°F) 4.3
Service Temperature, °C 200

ELECTRICAL PROPERTIES:

Dielectric Constant, 1 kHz, ASTM-D-150 2.95

USE INSTRUCTIONS:

1. Pre-mix contents of each container before use to ensure the entire contents are uniform. Some separation may occur upon prolonged storage, which is soft and easily incorporated. SOLAR COMPOUNDS recommends mixing each component using a half-inch electric drill and Jiffy Mixing Blade for at least 3 to 5 minutes before use.
2. Measure out equal components of the product by weight or volume and mix thoroughly together until a uniform color is observed without streaks.

CURE SCHEDULE:

Initial cure is achieved in 24-48 hours at room temperature. Final cure takes at least 7-10 days at 72°F. To accelerate the cure, higher temperatures can be used; 150°F is usually sufficient.

SPECIAL REQUIREMENTS:

1. This product has a tendency to separate upon storage and shipment; material should be mixed well prior to use. Store in a cool dry place.
2. Silicones can be poisoned by foreign contaminants like sulphur and amine compounds. Poisoning inhibits the cure of the silicone at the point of contact with the contaminant. Increasing the catalyst used, speeding up the cure time, or removing contaminants from the process can stop poisoning.
3. Supplied in 5-gallon and 55-gallon containers.

IMPORTANT:

The following supersedes any provision in your company's forms, letters, and papers. **SOLAR COMPOUNDS CORPORATION** makes NO WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES of MERCHANTABILITY OR of FITNESS FOR A PARTICULAR PURPOSE FOR THIS PRODUCT. No statements or recommendations contained in the product literature are to be construed as inducements to infringe any relevant patent, now or thereafter in existence. UNDER NO CIRCUMSTANCES SHALL **SOLAR COMPOUNDS CORPORATION** BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL OR OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH of WARRANTY, STRICT LIABILITY OR ANY OTHER THEORY, ARISING OUT of THE USE OR HANDLING of THIS PRODUCT. The sole liability of **SOLAR COMPOUNDS CORPORATION** for any claims arising out of the manufacture, use or sale of its products shall be to refund the buyer's purchase price, provided such products have been demonstrated in **SOLAR COMPOUNDS CORPORATION'S** sole opinion, to justify such refund.

HEALTH CAUTION:

Please refer to Material Safety Data Sheet before using these products.

PLEASE REFER TO MATERIAL SAFETY DATA SHEET FOR FURTHER FIRST AID INFORMATION.

FOR CHEMICAL EMERGENCY
CALL CHEMTREC (DAY OR NIGHT) 800-424-9300.